🐝 martini

Martini DELUXE

Sound absorptive rigid board with no fabric



CSR



dECO Deluxe

- High end ceiling or wall finish.
- Sound absorptive board across a range of frequencies.
- Board for fabric wrapping.
- Direct fix installation.

Applications

Rigid board for interior wall and ceiling panelling, workstation partitions and pinboards in spaces such as offices, meeting rooms, theatres, restaurants, libraries, classrooms, sports halls and auditoriums.

Decorative Finishes

dECO Deluxe can be fabric faced or fabric wrapped to complement the decor of any environment and can be used as a functional decorative feature wall. For other finishing options, consult your CSR Martini representative.

Environmental Benefits and Credentials

Manufactured from thermally bonded polyester fibre with up to 80% recycled fibre content from post-consumer PET packaging such as empty drink bottles.

- GreenTag^{CertTM} certified
- Environmental Product Declaration (EPD) Certified in accordance with ISO 14025
- Product Health Declaration (PHD) certified
- Declare certified
- Suitable for Green Star[™] projects
- No red list chemicals are present
- No ozone-depleting gases are used during the manufacturing process
- Volatile organic compounds (VOCs) generated in the manufacturing process is classified as low (0.01 mg/m³)s
- · Safe, non-irritant, non-toxic, and non-allergenic
- Products are 100% recyclable
- High reuse potential



Martini's Product Stewardship Program can be viewed at www.csrmartini.com.au

Acoustic Performance

Frequencies	125hz	250hz	500hz	1,000hz	2,000hz	4,000hz	NRC
24mm	0.05	0.20	0.55	0.85	0.95	0.95	0.65
48mm	0.20	0.65	0.95	1.00	1.00	0.95	0.90

Tested in accordance with AS/ISO 354:2006.

Product Specifications

Product	Thickness (mm)	Length (mm)	Width (mm)	Boards /box	m² /pack	Code
dECO Deluxe White	24	2410	1210	2.92	4	156877
dECO Deluxe Black	24	2410	1210	2.92	4	156878
dECO Deluxe White	48	2410	1210	2.92	2	157010
dECO Deluxe Black	48	2410	1210	2.92	2	157011

Tolerance in sizes: thickness +/- 2mm; length +/- 10mm; width +/- 5mm



Physical description and properties

Melting point:	250°C					
Flash point:	None allocated					
Other properties:	Non-allergenic, low irritant, low flame response, resilient					
Ingredients:	Organic, long chain synthetic polymer					
Max service temp:	110°C					
Alkalinity:	pH 7.8 (pH 7 is neutral)					
Moisture absorption:	Exposure to an atmosphere of 50°C and 95% RH for four days gives moisture absorption of less than 0.2% by volume					
Fire resistance:	Tested to AS ISO 9705 Corner Burn in accordance with AS 5637.1	Group 1 SMOGRA not more than 100m²/s² x 1000				
	The following results were obtained when CSR Martini dECO Deluxe was subjected to early fire hazard testing in accordance with Australian Standards AS 1530.3	Ignitability Spread of Flame Heat Evolved Smoke Developed	0 0 0-1			

csrmartini.com.au

CSR Martini Pty Limited P.O. Box 560, Ingleburn NSW 1890 martinienquiries@csr.com.au 1300 767 776

04/19









Disclaimer: The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Martini. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the CSR Martini website for the latest version of this document. The purchaser should independently determine the suitability of the product for the intended use and application.