



Martini ABSORB

High performance sound absorptive insulation

A large, light blue, stylized lowercase letter 'm' graphic that spans the bottom half of the page.

CSR

Martini Absorb

- Thermally bonded polyester fibre insulation specifically designed to provide high performance sound absorption across a range of frequencies.
- Made in a range of densities and thicknesses with fibre blends specifically engineered to provide maximum thermal and acoustic performance in many diverse commercial, residential, community and industrial applications.
- Non-irritant and does not require any protective clothing or masks during installation.
- Available in standard white colour. Black or grey available upon request.

Applications

Absorb is ideal for use behind perforated panelling and ceilings in sports halls, cinemas, studios, industrial enclosures, HVAC ducts, silencers or plant rooms. It is highly effective at reducing echo in rooms and provides consistent sound absorption across the speech range frequencies. Absorb can also be laid above suspended ceilings to reduce flanking noise between rooms.

Absorb can also be used behind decorative woven fabrics as acoustic panels or baffles to cut reverberation and echo in commercial areas where hard surfaces predominate and cause unwanted noise.

Environmental Benefits and Credentials

Manufactured from thermally bonded polyester fibre with up to 80% recycled fibre content from post-consumer PET packaging such as empty drink bottles.

- GreenTag^{Cert}™ certified
- Environmental Product Declaration (EPD) Certified in accordance with ISO 14025
- Product Health Declaration (PHD) certified
- Declare certified
- Suitable for Green Star™ projects
- No red list chemicals are present
- No ozone-depleting gases are used during the manufacturing process
- Volatile organic compounds (VOCs) generated in the manufacturing process is classified as low (0.01 mg/m³)s
- Safe, non-irritant, non-toxic, and non-allergenic
- Products are 100% recyclable
- High reuse potential



Martini's Product Stewardship Program can be viewed at www.csrmartini.com.au

Acoustic Performance

Frequencies	125hz	250hz	500hz	1,000hz	2,000hz	4,000hz	Alpha W	NRC
MD 25	0.14	0.33	0.59	0.79	0.84	0.89	0.60	0.65
MD 50	0.24	0.54	0.90	0.98	1.01	1.06	0.85	0.85
HD 25	0.12	0.29	0.62	0.78	0.91	0.92	0.60	0.65
HD 50	0.22	0.54	1.02	1.07	1.04	1.11	0.90	0.95
HD 75	0.41	0.85	1.15	1.11	1.07	1.16	1.00	1.05
HD 100	0.54	1.12	1.13	0.97	0.94	0.99	1.00	1.00
XHD 25*	0.15	0.35	0.60	0.80	0.85	0.95	0.70	0.70
XHD 50	0.19	0.62	1.01	1.02	0.98	0.96	0.90	0.90
XHD 75*	0.45	0.80	1.00	1.00	1.00	1.00	1.00	1.00
XHD 100	0.60	1.18	1.15	0.99	1.00	1.01	1.00	1.10
XXHD 30	0.11	0.42	0.76	0.89	0.86	0.88	0.70	0.70
XXHD 50	0.25	0.65	0.95	0.95	0.95	0.95	0.95	0.90
XXHD 75	0.40	0.87	0.96	0.95	0.87	0.89	1.00	0.95

Tested in accordance with AS/ISO 354:2006. *Opinion derived from empirical data.

Flow Resistivity

Tested in accordance with ASTM C 522-03

Product	Absorb HD	Absorb XHD	Absorb XXHD
MKS RAYL/M	7,994	14,693	21,008

Product Specifications

Product	Thickness (mm)	Length (mm)	Width (mm)	Sheets /pack	m ² /pack	R value	White code	Black code
MD 25	25	2400	1200	12	34.56	0.6*	130537	133525
MD 50	50	2400	1200	6	17.28	1.2*	130538	133526
MD 75	75	2400	1200	4	11.52	1.9*	130539	133527
MD 100	100	2400	1200	3	8.64	2.5*	130540	133528
HD 25	25	2400	1200	12	34.56	0.7*	130541	133529
HD 50	50	2400	1200	6	17.28	1.4*	130542	133530
HD 75	75	2400	1200	4	11.52	2.1*	130543	133531
HD 100	100	2400	1200	3	8.64	2.7*	130544	133532
XHD 25	25	2400	1200	10	28.80	0.7*	130567	133533
XHD 50	50	2400	1200	6	17.28	1.5*	130546	133472
XHD 75	75	2400	1200	4	11.52	2.2*	130547	133534
XHD 100	100	2400	1200	3	8.6	3.0*	130548	131953
XXHD 30	30	2400	1200	6	28.8	1.0*	141444	141445
XXHD 50	50	2400	1200	3	8.64	1.5*	141443	153352
XXHD 75	75	2400	1200	2	5.76	2.2*	153355	153353

*Calculated R-Value (Km²/W)

Physical description and properties

Flash point: None allocated

Other properties: Non-allergenic, low irritant, low flame response, resilient

Ingredients: Organic, long chain synthetic polymer

Max service temp: 150°C

Alkalinity: pH 7.8 (pH 7 is neutral)

Moisture absorption: Exposure to an atmosphere of 50°C and 95% RH for four days gives moisture absorption of less than 0.2% by volume

**Tested to AS ISO 9705 Corner Burn
in accordance with AS 5637.1**

Group 1
SMOGRA not
more than
100m²/s² x 1000

Fire resistance:

The following results were obtained when CSR Martini Absorb was subjected to early fire hazard testing in accordance with Australian Standards AS 1530.3

Ignitability	0
Spread of Flame	0
Heat Evolved	0
Smoke Developed	0-1

csrmartini.com.au

CSR Martini Pty Limited
P.O. Box 560, Ingleburn NSW 1890
martinienquiries@csr.com.au
1300 767 776

04/19



Disclaimer: The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Martini. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the CSR Martini website for the latest version of this document. The purchaser should independently determine the suitability of the product for the intended use and application.