



Martini dECO FLEX

Flexible fabric faced panel

A large, light blue, stylized lowercase letter 'm' graphic that spans the bottom half of the page.

CSR

dECO Flex 7mm

- Flexible wall finish for straight and curved walls.
- Velcro® receptive surface.

Applications

Used in operable wall construction as a lining.

Decorative Finishes

dECO Flex is available in dECO Captivate fabric. dECO Captivate is a non-woven fabric with nap and no pattern repeat. Refer to our dECO Captivate Colour Guide for colour palette options.

Environmental Benefits and Credentials

Manufactured from thermally bonded polyester fibre with up to 80% recycled fibre content from post-consumer PET packaging such as empty drink bottles.

- GreenTag^{Cert™} certified
- Environmental Product Declaration (EPD) Certified in accordance with ISO 14025
- Product Health Declaration (PHD) certified
- Declare certified
- Suitable for Green Star™ projects
- No red list chemicals are present
- No ozone-depleting gases are used during the manufacturing process
- Volatile organic compounds (VOCs) generated in the manufacturing process is classified as low (0.01 mg/m³)s
- Safe, non-irritant, non-toxic, and non-allergenic
- Products are 100% recyclable
- High reuse potential



Martini's Product Stewardship Program can be viewed at www.csrmartini.com.au

Product Specifications

Product	Thickness (mm)	Width (m)	Roll Length (m)*	Code
Apple	7	1220	25	166930
Ash	7	1220	25	166909
Citrus	7	1220	25	166967
Eggplant	7	1220	25	166969
Granite	7	1220	25	166906
Ice	7	1220	25	166905
Linen	7	1220	25	166921
Midnight	7	1220	25	166910
Moss	7	1220	25	166961
Nashi Pear	7	1220	25	166922
Nordic Sky	7	1220	25	166962
Ocean	7	1220	25	166964
Platinum	7	1220	25	166908
Rosso	7	1220	25	166968
Sapphire	7	1220	25	166965
Summit	7	1220	25	166963
Wheat	7	1220	25	166966

Tolerance in sizes: thickness +/- 2mm; width +/- 5mm. *Please note that due to the nature of the manufacturing process, there is a 10% over or under supply. Other roll lengths available upon request. Minimum length 7m.

Physical description and properties

Melting point: 250°C

Flash point: None allocated

Other properties: Non-allergenic, low irritant, low flame response, resilient

Ingredients: Organic, long chain synthetic polymer

Max service temp: 110°C

Alkalinity: pH 7.8 (pH 7 is neutral)

Moisture absorption: Exposure to an atmosphere of 50°C and 95% RH for four days gives moisture absorption of less than 0.2% by volume

**Variations marked # Tested to AS ISO 9705
Corner Burn in accordance with AS 5637.1**

Group 1
SMOGRA not
more than
100m²/s² x 1000

Fire resistance:

The following results were obtained when CSR Martini dECO Flex was subjected to early fire hazard testing in accordance with Australian Standards AS 1530.3

Ignitability	0
Spread of Flame	0
Heat Evolved	0
Smoke Developed	0-1

csrmartini.com.au

CSR Martini Pty Limited
P.O. Box 560, Ingleburn NSW 1890
martinienquiries@csr.com.au
1300 767 776

04/19



Disclaimer: The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Martini. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the CSR Martini website for the latest version of this document. The purchaser should independently determine the suitability of the product for the intended use and application.